

PRODUCT DATA SHEET

X-CREPE-N
 GRADE 403030

PROPERTY

NOMINAL VALUES

| | | | |
|-----|--------------------------------------|-----------|------------------------|
| 1.) | COMPOSITION SULFATE WOOD PULP | | 100% |
| 2.) | UNCREPED WEIGHT (LBS/ REAM) | | 40# (+/- 5%) |
| 4.) | CREPED WEIGHT (LBS/ REAM) | | 71# (+/- 5%) |
| 5.) | THICKNESS (INCHES) | | .011" - .014" |
| 6.) | ELONGATION (%) | MD CMD | 30 30 |
| 7.) | TENSILE STRENGTH (MD) (LBS/ INCH) | CMD | 11 7 |
| 8.) | TEAR RESISTENCE (GRAMS) | MD CMD | 250 - 400 350 - 500 |

NOTE: ALL TEST IN ACCORDANCE WITH STANDARD TAPPI PROCEDURES.

ELONGATION AND TENSILE ARE AVERAGES AND CAN BE VARIED TO MEET CUSTOMERS NEEDS

60" MAXIMUM WIDTH OR SLIT TO DESIRED SIZE