

CINDUS

ELASTIKRAFT CREPED PAPER

Industrial Creped Products Division

GRADE (Partial listing)	Base Paper	ELASTIKRAFT Creped Paper				Additional Property
		Elongation %	Yield	Nominal Weight	Lbs/3000 sq.ft.	
	Weight Lbs/3000 sq.ft.	MD	Sq.ft./lb.			
130 B	30	15	87	35		
130 EF	30	30	77	39	Fine crepe	
140 DF	40	25	60	50	Fine crepe	
140 F	40	35	56	54	None	
140 G	40	40	54	56	None	
160 DF	60	25	40	75	Fine crepe	
160 EF	60	30	38	78	Fine crepe	
178 HF	78	45	27	113	Fine crepe	
230 D	30	25	70	43	Waxed	
350 EF	50	30	46	65	Fine crepe	
360 DF	60	25	41	75	Fine crepe	
360 HF	60	45	34	87	Fine crepe	
560 E	60	30	35	85	Release ctd.	

GRADE SYSTEM FOR ELASTIKRAFT

FIRST DIGIT:

1. Unwaxed kraft
2. Waxed kraft
3. Unwaxed bleached kraft
4. Waxed bleached kraft
5. Release coated kraft
6. Release coated bleached kraft

SECOND TWO DIGITS:

Uncreped Basis Weight

SUFFIX: [stretch indicator]

	elongation	range
A	10%	10 to 15%
B	15%	15 to 20%
C	20%	20 to 25%
D	25%	25 to 30%
E	30%	30 to 35%
F	35%	35 to 40%
G	40%	40 to 45%
H	45%	Over 45%