



(513) 948-8800
FAX (513) 948-8805

CINDUS CORPORATION

CORPORATE OFFICES

515 Station Avenue / Cincinnati, Ohio 45215

MILITARY PACKAGING

Specification
MIL-PRF-121G, Type I, Medium Duty

Material construction - 60 # kraft / 28 # PE

Physical Properties:

Test	Test Method	Unit of Measure	Nominal Value
Tensile Breaking Strength:	Tappi T404	lbs/inch width	
MD			40
CMD			28
Tearing Resistance:	Tappi T414	grams	
MD paper side			180
MD film side			170
CMD paper side			165
CMD film side			160
Bursting Strength:	Tappi T403	psi	52
Caliper:	Tappi T411	mils	7.5
Yield:		in ² /lb	4900
Seal Strength: @ 525° F, 60 psi, 3 sec.	Tappi T404		5.0
Puncture Resistance	FED-STD-101 Method No. 2065	lbs.	6.5