

PRODUCT DATA SHEET  
 X-CREPE-N  
 GRADE 403030 - PERFORATED

PROPERTY	NOMINAL VALUES
1.) COMPOSITION SULFATE WOOD PULP	100%
2.) UNCREPED WEIGHT (LBS/ REAM)	40# (+/- 5%)
3.) CREPED WEIGHT (LBS/ REAM)	71# (+/- 5%)
4.) THICKNESS (INCHES)	.011" - .013"
5.) ELONGATION (%) MD CMD	27 - 32 27 - 32
6.) TENSILE STRENGTH (MD) (LBS/ INCH) CMD	13 8
7.) AIR RESISTENCE MD (SEC/ 100CC) CMD	2.0
8.) DENSITY (G/ CC)	0.40
9.) YIELD (SQ. YD./ LB.)	4.27

NOTE: ALL TEST IN ACCORDANCE WITH STANDARD TAPPI PROCEDURES.

60" MAXIMUM WIDTH OR SLIT TO DESIRED SIZE. 36" MAXIMUM O.D.